

PRODUCT: 62 PSA REV031423NT

PRODUCT DESCRIPTION: Pressure sensitive adhesive backing.

Physical Property	Description - Value
Material	Acrylic
Туре	Polyester Scrim
Liner Type	Silicone-coated Polypropylene film, white
Thickness	2 mil (0.04 - 0.06 mm)
Temperature Resistance	-22 to 248 °F (-30 to 120 °C)

Peel Adhesion Tests: 23 µm PET, 180° Peel angle, 300 mm/min Peel speed, 25 mm tape width, 73 °F

Dwell	Material	Results
	Powder-coated Aluminum	2570 lb/in (450 N/mm)
1 min	Glass	2430 lb/in (425 N/mm)
	Polypropylene	2430 lb/in (425 N/mm)
	Steel	2570 lb/in (450 N/mm)
10 min	Glass	2570 lb/in (450 N/mm)
	Steel	2570 lb/in (450 N/mm)
24 hours	Glass	2710 lb/in (475 N/mm)
	Steel	2570 lb/in (450 N/mm)

Test	Requirements	Results
Static Shear Adhesion	23 μm PET, 625 mm <sup>2</sup> area, @73 °F, 1 hr. dwell	28.0 lb/in (4.90 N/mm)
Shear Adhesion Failure	23-micron PET, 1 hr. dwell, 625 mm <sup>2</sup> area, 40 g/m <sup>2</sup>	270 °F (132 °C)
Temperature (SAFT)	adhesive coating weight, 1.8 °F/min ramp rate	

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement, or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Industries' knowledge or obtained from sources believed by Technicon Industries to be accurate, and Technicon Industries does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.