

**PRODUCT: 94 PSA**

**REV071023NT**

**PRODUCT DESCRIPTION:** Unsupported acrylic pressure sensitive adhesive.

Physical Property	Description - Value	Test Standard
Material	Acrylic	
Type	Unsupported	
Thickness	4 mil (0.10 mm)	
Liner Type and Thickness	74 lb Kraft Paper, 5.5 mil (0.14 mm)	
Peel Adhesion, 1 mil Polyester	4.1 lb/in (0.72 N/m)	PSTC #101, 24 Hr Dwell
Peel Adhesion, 2 mil dead soft aluminum foil	10. lb/in (1.75 N/m)	PSTC #101, 24 Hr Dwell
Shear Adhesion, 1 minute Max Dwell	7 days	PSTC #107 @72 °F, 1000 g/in <sup>2</sup>
Shear Adhesion, 1 minute Max Dwell	7 days	PSTC #107 @150 °F, 500 g/in <sup>2</sup>
Temperature Range	-30 to 220 °F (-34 to 104 °C)	Intermittent to 250 °F (121 °C)

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement, or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Industries' knowledge or obtained from sources believed by Technicon Industries to be accurate, and Technicon Industries does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.