

**PRODUCT:**

**98 PSA**

**REV082415**

**PRODUCT DESCRIPTION:**

Double coat, supported, acrylic pressure sensitive adhesive

**PSA**

Physical Property	Description - Value	Test Standard
Material	Acrylic	
Type	Supported	
Adhesive Thickness-Exposed Side	1.7 mils +/- 10%	
Adhesive Thickness-Liner Side	1.3 mils +/- 10%	
Peel Adhesion-Exposed Side	99 oz/inch width	PSTC#101 Method C, backed with 1 mil polyester
Peel Adhesion-Liner Side	94 oz/inch width	PSTC#101 Method C, backed with 1 mil polyester
Peel Adhesion – Exposed Side	220 oz/inch width	PSTC#101 Method C, backed with 2 mil dead soft aluminum foil
Peel-Adhesion – Liner Side	210 oz/inch width	PSTC#101 Method C, backed with 2 mil dead soft aluminum foil
Shear Adhesion-Exposed Side	4+ days	PSTC#107 Procedure A, Modified; 1000 grams/square inch, one minute dwell
Shear Adhesion-Liner Side	7+ days	PSTC#107 Procedure A, Modified; 1000 grams/square inch, one minute dwell
Temperature range	-30 °F to 220 °F	ASTM D4498-00, Modified, 24-hour dwell, 1"X 1"X 500 grams
Carrier	0.5 mil PET	
Liner	74 lb, 5.5 mils, white coated Kraft	

**AVAILABLE SIZES**

Roll	54" X 300 LY
Sheet	As Specified

**Compliance Features:**

- Meets the Requirements of RoHS through June 2013 Revision of SVHC (Restriction of Hazardous Substances European Union Directive – 2002/95/EC)
- Compliant with European Union REACH (Registration, Evaluation and Authorization of Chemical Substances - EC1907/2006)

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Acoustics knowledge or obtained from sources believed by Technicon Acoustics to be accurate, and Technicon Acoustics does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.