

PRODUCT: AF-051

REV050123NT

PRODUCT DESCRIPTION: Acoustic vinyl nitrile closed cell foam.

Physical Property	Description - Value	Test Methods
Material	Nitrile Butadiene, Polyvinyl Chloride blend	
Color	Black	
Available Thicknesses	0.125 in (3.18 mm) – 2.0 in (51 mm)	N/A
Density	3-6 lb/ft ³ (471-943 N/m ³)	ASTM D 1667
Dimensional Stability	<7% Linear Shrinkage	ASTM C 534
Flexibility	Excellent, Pass: Cold Crack Test at -40 °F (-40 °C)	ASTM C 534 & ASTM D 1056
Hot Surface Performance	No Cracking or Delamination	ASTM C 411
Thermal Conductivity Btu-in/hr-Ft ² -°F (W/mK)	90 °F Mean Temp = 0.258 (0.0372) 75 °F Mean Temp = 0.245 (0.0353) 32 °F Mean Temp = 0.235 (0.0339)	ASTM C 177
Operating Temperature Range	-40 to 200 °F (-40 to 93 °C)	ASTM C 534
Flame Spread / Smoke Development (up to 2 in wall)	< 25/50	ASTM E 84
Flammability	Self-Extinguishing Pass Pass Pass Pass	ASTM D 635 FMVSS 302 UL 94-5V UL 94-V0 FAR 25.853
Water Vapor Permeability (Dry Cup)	< 0.01 perm-in	ASTM E 96
Water Absorption (Volume Change)	0%	ASTM C 209
Leachable Chlorides	< 0.05% water-soluble chloride ions	DIN 1988
Corrosion Risk	pH neutral: 6.6 +/- 0.04	DIN 1988
Chemical/Solvent/Oil/Grease Resistance	Good	Compatibility Data Available on Request
Ozone Resistance	Pass	ASTM D 1171
Odor Emissions	No Objectionable Odor	ASTM C 1304
UV / Weather Resistance	Good	ASTM G 90
Mildew Growth Resistance/Air Erosion	Pass	UL 181, ASTM G 21
Sound Transmission Class	13	ASTM E 90

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Industries' knowledge or obtained from sources believed by Technicon Industries to be accurate, and Technicon Industries does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.