

**PRODUCT: DM-200-00-00-97**

**REV041317**

**PRODUCT DESCRIPTION:** PVC damping sheet with pressure sensitive adhesive.

**DAMPING BASE**

Physical Property	Description - Value
Material	PVC vinyl (polyvinylchloride)
Color	Charcoal
Density	1 g/cc
Thickness	0.05 inch
Service Temperature	-40°F to 220°F
Chemical Resistance	Excellent for most acids, mild alkalis, oils and grease

**ADHESIVE**

Physical Property	Description - Value	Tolerance	Test Standard
Material	Acrylic		
Type	Unsupported		
Thickness	3 mils	+/- 0.3 mil	
Thickness – PET Release Liner	2 mils		
Peel Adhesion – Exposed Side	50 oz/inch width initial		PSTC #101 Method E, backed with 1 mil polyester, 24 hr dwell
Liner	2-mil Silicone coated polyester liner		
Shear Adhesion – Exposed Side	168 Hours		PSTC#107, Procedure A, Modified; 1000gm/sq.in at 72°F, 1 min dwell
Shear Adhesion	18 Hours		PSTC#107, Procedure A, modified; 1000gm/sq. in at 150°F, 1 min dwell
Temperature Range	-30° to 220°F		

**DAMPING PERFORMANCE**

Temperature	-18 C, 0 F	-9 C 18 F	0 C 32 F	9 C 48 F	18 C 64 F	27 C 81 F	36 C 97 F	45 C 113 F	54 C 129 F
Average Loss Factor	0.10	0.18	0.29	0.34	0.37	0.33	0.22	0.15	0.11

**AVAILABLE SIZES**

Roll	54" X 25'
Sheet	As Specified
Tile	1' X 1'



THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Industries' knowledge or obtained from sources believed by Technicon Industries to be accurate, and Technicon Industries does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.

**Average Damping Loss Factor  
DM-300  
SAE Bar**

