

PRODUCT: DMF-201-X0-UB-57

REV071023NT

PRODUCT DESCRIPTION: PVC damping sheet with acoustic polyester foam, black urethane film facing, and pressure sensitive adhesive.

FACING

Physical Property	Description - Value	Test Method
Material	Polyester Polyurethane film/sheet	
Gauge Available	2 mil (0.508 mm)	
Specific Gravity	1.21	ASTM D 792
Shore A Durometer	92	ASTM D 2240
Ultimate Tensile Strength	11,000 psi (75.8 MPa)	ASTM D 882
Ultimate Elongation	500%	ASTM D 882
100% Modulus (MD/CD Avg.)	1,700 psi (11.7 MPa)	ASTM D 882
300% Modulus (MD/CD Avg.)	5,000 psi (34.5 MPa)	ASTM D 882
Tear Resistance (MD/CD Avg.)	500 lb/in (87.6 kN/m)	ASTM D 1004

DAMPER

Physical Property	Description - Value
Material	Polyvinyl Chloride (PVC)
Color	Charcoal Gray
Density	62.4 lb/ft ³ (9.80 N/m ³)
Thickness	0.05 in (1.27 mm)
Service Temperature	-40 to 220 °F (-40 to 104 °C)
Chemical Resistance	Excellent for most acids, mild alkalis, oils and grease

FOAM

Physical Property	Description - Value	
Material	Polyester Polyurethane Foam	
Color	Charcoal	
Available Thicknesses	0.125 in (3.18 mm) - 4.0 in (102 mm)	
Density	2.00 lb/ft ³ (314 N/m ³) +/- 0.10%	
	Minimum	Average
Tensile Strength	18.0 psi (124 kPa)	25.0 psi (172 kPa)
Elongation	170%	220%
Tear Resistance	2.00 lb/in (3.50 N/cm)	2.50 lb/in (4.37 N/cm)
Compression Force Deflection 25% Deflection	0.40 psi (2.8 kPa)	0.50 psi (3.4 kPa)
Compression Force Deflection 50% Deflection	0.45 psi (3.1 kPa)	0.60 psi (4.1 kPa)
Compression Set @ 50%	8% maximum	
Retention of Tensile Strength after 3 hours, 105°C, Steam Autoclave	70% minimum	
Retention of Tensile Strength after 22 hours, 140°C, Dry Heat Aging	70% minimum	
Pores per inch	55 +/- 5	
Flammability	FMVSS 302, UL 94 HF-1	

Test Methods: ASTM-D3574-[latest revision]. Standard Methods of Testing Flexible Cellular Materials – Slab, Bonded, and Molded Urethane Foam.



ADHESIVE

Physical Property	Description - Value
Material	Low Surface Energy Acrylic
Type	Thin PET film backed PSA
Liner Type	PET Film
Adhesive Thickness	2 mil (0.0508 mm)
Liner Thickness	2 mil (0.0508 mm)
Peel Adhesion 20 min, 180 ° off Stainless Steel	6.22 lb/in (1.09 N/mm)
Loop Tack	8.11 lb/in (1.42 N/mm)
Temperature Resistance	-30 to 250 °F (-34 to 121 °C)

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement, or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Industries' knowledge or obtained from sources believed by Technicon Industries to be accurate, and Technicon Industries does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.

