

**PRODUCT: -FS-**

**REV061323NT**

**PRODUCT DESCRIPTION:** Fiber Scrim facing.

Physical Property	Description - Value		Test Method
Material	Proprietary blend of PET/CV		
Coating	Low Density Polyethylene		
Color	Charcoal & Black		
Thickness	16 +/- 8 mil (0.4 +/- 0.2 mm)		ASTM D 5729
Total Weight	0.012 lb/ft <sup>2</sup> (0.57 N/m <sup>2</sup> )		
	<b>Machine Direction</b>	<b>Cross Direction</b>	
Tensile Strength	3.4 lb/in (≥6 N/cm)	4.5 lb/in (≥8 N/cm)	ASTM D 5035
Elongation	≥15%	≥25%	ASTM D 5035

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Industries' knowledge or obtained from sources believed by Technicon Industries to be accurate, and Technicon Industries does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.