

PRODUCT:

-PC-

REV052323NT

PRODUCT DESCRIPTION: Perforated Black 14% Open Area (Crush).

Physical Property	Description - Value		Test Method
Material	Vinyl Polyester blend		
Coating Type	Single coated flexible vinyl		
Basis Weight	0.12 lb/ft ² (5.7 N/m ²)		ASTM D 751
Thickness	20 mil (0.51 mm)		ASTM D 751
	Warp	Fill	
Grab Tensile	80 lb (356 N)	78 lb (347 N)	ASTM D 751
Trapezoid Tear	12 lb (53 N)	14 lb (62 N)	ASTM D 751
Adhesion	20 lb/in (226 N/cm)	18 lb/in (203 N/cm)	ASTM D 751
Sealing Properties	Dielectric & Thermal		

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Industries' knowledge or obtained from sources believed by Technicon Industries to be accurate, and Technicon Industries does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.