

PRODUCT:

PF-091-X0-00-33

REV011719

PRODUCT DESCRIPTION:

Fire resistant fiber with pressure sensitive adhesive

FIBER

Physical Property	Description - Value	Tolerance
Material	FR Fiber blend	
Thicknesses (nominal)	0.5", 1.0", 1.5", 2.0"	+/- 20%
Color	Grey	
Service Temperature	-40 °F – 350 °F	
Flammability	Passes MVSS 302, UL94 HF1, UL HBF	

PSA

Physical Property	Description - Value	Test Standard
Material	Acrylic	
Type	Scrim supported	
Thickness	3.1 mils	
Peel Adhesion, 23 micron Polyester	57.6 oz/in	1 min Dwell, Powder-coated Aluminum
Peel Adhesion, 23 micron Polyester	60.7 oz/in	1 min Dwell, Glass
Peel Adhesion, 23 micron Polyester	57.6 oz/in	1 min Dwell, Polypropylene
Peel Adhesion, 23 micron Polyester	100.8 oz/in	24 hr Dwell, Steel
Shear Adhesion, 23 micron Polyester	500g/mm	@73 °F, 1 hr dwell, 625 mm ² area
Temperature Resistance	-30 °F to 250 °F	Intermittent to 270 °F
Liner type and thickness	Paper, 3 mil	

AVAILABLE SIZES

Roll	54" X 100'
Sheet	As Specified
Cut parts	Customer specified

Compliance Features:

- **UL94 HF-1 Listed File no. E504782**
- Meets the Requirements of RoHS through June 2013 Revision of SVHC (Restriction of Hazardous Substances European Union Directive – 2002/95/EC)
- Compliant with European Union REACH (Registration, Evaluation and Authorization of Chemical Substances - EC1907/2006)

*THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Industries' knowledge or obtained from sources believed by Technicon Industries to be accurate, and Technicon Industries does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.

ABSORPTION COEFFICIENT, NRC and SAA to ISO 354

Frequency	Sound Absorption Coefficient
(Hz)	α_s
100	0.19
125	0.25
160	0.30
200	0.29
250	0.42
315	0.46
400	0.57
500	0.62
630	0.68
800	0.69
1000	0.79
1250	0.82
1600	0.82
2000	0.78
2500	0.79
3150	0.81
4000	0.81
5000	0.80
NRC	0.65
SAA	0.64

CONFIDENTIAL

ISO 354:2003 - Sound Absorption in Reverb Room

Test ID: 354-102318-1

Product Description: PF-091-40-00-00

Manuf: Technicon, Thickness: 25.4mm,

Mounting: Type A

