

PRODUCT:

TECH DAMP FD-100

REV053117

PRODUCT DESCRIPTION: TECH DAMP FD-100 Vibration Damping material is a constrained layer damping foam composite with pressure sensitive adhesive on the back.

DAMPING BASE

Physical Property	Description - Value
Material	Constrained Layer Damping Foam
Color	Silver
Density	.207 g/cc, .22lbs/sq.ft Areal Density
Thickness	.130"
Service Temperature	-40°F to 250°F (-40 °C to 70 °C)
Chemical Resistance	Excellent for most acids, mild alkalis, oils and grease
Flammability	Passes FAR 25.853(a) and UL-HBF

DAMPING PERFORMANCE to ASTM E756 (Resonance 2 through 4 Average)

Temperature	-18 C, 0 F	-9 C 18 F	0 C 32 F	9 C 48 F	18 C 64 F	27 C 81 F	36 C 97 F	45 C 113 F	54 C 129 F
Average Loss Factor	0.038	0.058	0.12	0.23	0.41	0.92	0.44	0.86	0.74

Compliance Features:

- Meets the Requirements of RoHS through June 2013 Revision of SVHC (Restriction of Hazardous Substances European Union Directive – 2002/95/EC)
- Compliant with European Union REACH (Registration, Evaluation and Authorization of Chemical Substances - EC1907/2006)

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Industries' knowledge or obtained from sources believed by Technicon Industries to be accurate, and Technicon Industries does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.

Average Damping Loss Factor

SAE Bar

