

PRODUCT: -UB-

REV031323NT

PRODUCT DESCRIPTION: Black Urethane film facing.

Physical Property	Description - Value	Test Method
Material	Polyester Polyurethane film/sheet	
Gauge Available	2 mil (0.508 mm)	
Specific Gravity	1.21	ASTM D 792
Shore A Durometer	92	ASTM D 2240
Ultimate Tensile Strength	11,000 psi (75.8 MPa)	ASTM D 882
Ultimate Elongation	500%	ASTM D 882
100% Modulus (MD/CD Avg.)	1,700 psi (11.7 MPa)	ASTM D 882
300% Modulus (MD/CD Avg.)	5,000 psi (34.5 MPa)	ASTM D 882
Tear Resistance (MD/CD Avg.)	500 lb/in (87.6 kN/m)	ASTM D 1004

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Industries' knowledge or obtained from sources believed by Technicon Industries to be accurate, and Technicon Industries does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.