

PRODUCT: **VPF-351-01-DF-00** **REV051616**

PRODUCT DESCRIPTION: 1 lb/sf PVC barrier with 1/4 inch Nitrile/PVC decoupler and black diamond PVC wear surface.

BARRIER

Physical Property	Description - Value
Material	Flexible PVC vinyl (polyvinylchloride)
Color	Charcoal gray
Specific Gravity	1.8 g/cc
Flammability	MVSS-302
Service Temperature	-40°F to 220°F
Chemical Resistance	Excellent for most acids, mild alkalis, oils and grease

FOAM

Physical Property	Description - Value	Standard	Tolerance
Material	Nitrile/PVC		
Color	Black		
Classification	2C1	ASTM D1056	
Density	4.5 lb/cf	ASTM D1056	+/- 1 lb/cf
Flammability	0 Burn Rate	FMVSS302	
Tensile Strength	40 psi	ASTM D412	Minimum
Elongation	100%	ASTM D412	Minimum
25% Compression Resistance	2.75 psi	ASTM D1056	+/- 0.75 psi
Water Absorption	10%	ASTM D1056	Max

FACING

Physical Property	Description - Value	Test Standard
Material	PVC	
Hardness	85 Shore A Durometer +/- 5	ASTM D2240
Elongation	125% minimum	ASTM D412
Tensile Strength	600 PSI minimum	ASTM D412
Tear Strength – Die “C”	125 lbs	ASTM D412

ACOUSTICAL PROPERTIES

ASTM E90 and E413 on 1 lb/sf barrier only

Frequency (Hz)	125	250	500	1000	2000	4000	STC
TL (dB)	17	19	24	29	34	40	28

AVAILABLE SIZES

Roll	54" X 25'
Sheet	As Specified

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Industries' knowledge or obtained from sources believed by Technicon Industries to be accurate, and Technicon Industries does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.