

**PRODUCT: VBF-X01-0X-DF-00**

**REV071023NT**

**PRODUCT DESCRIPTION:** PVC barrier with acoustic polyester foam decoupler layer and diamond patterned rubber wear surface.

## FACING

Physical Property	Description - Value	Test Method
Material	Proprietary Vinyl Blend	
Color	Black	
Surface Finish	Diamond pattern	
Back Finish	Textured cloth impression	
Thickness	0.15625 in (4.0 mm)	ASTM D 412
Durometer (Shore A)	80 +/- 5	ASTM D 2240
Tensile Strength	600 psi (4.1 MPa)	ASTM D 412
Elongation	150%	ASTM D 412
Tear Resistance (Die C)	100 lb/in (1130 N/cm)	ASTM D 412

## BARRIER

Physical Property	Description - Value
Material	Flexible Polyvinylchloride (PVC vinyl)
Color	Charcoal Gray
Specific Gravity	112 lb/ft <sup>3</sup> (1800 kg/m <sup>3</sup> )
Weight Range	0.5 to 2.0 lb/ft <sup>2</sup> (2.4 to 9.8 kg/m <sup>2</sup> ) +/- 10%
Flammability	FMVSS 302
Service Temperature	-40 to 220 °F (-40 to 104 °C)
Chemical Resistance	Excellent for most acids, mild alkalis, oils, and grease

## DECOUPLER

Physical Property	Description - Value	
Material	Polyester Polyurethane Foam	
Color	Charcoal	
Available Thicknesses	0.125 in (3.18 mm) - 4.0 in (102 mm)	
Density	2.00 lb/ft <sup>3</sup> (314 N/m <sup>3</sup> ) +/- 0.10%	
	<b>Minimum</b>	<b>Average</b>
Tensile Strength	18.0 psi (124 kPa)	25.0 psi (172 kPa)
Elongation	170%	220%
Tear Resistance	2.00 lb/in (3.50 N/cm)	2.50 lb/in (4.37 N/cm)
Compression Force Deflection 25% Deflection	0.40 psi (2.8 kPa)	0.50 psi (3.4 kPa)
Compression Force Deflection 50% Deflection	0.45 psi (3.1 kPa)	0.60 psi (4.1 kPa)
Compression Set @ 50%	8% maximum	
Retention of Tensile Strength after 3 hours, 105°C, Steam Autoclave	70% minimum	
Retention of Tensile Strength after 22 hours, 140°C, Dry Heat Aging	70% minimum	
Pores per inch	55 +/- 5	
Flammability	FMVSS 302, UL 94 HF-1	

Test Methods: ASTM-D3574-[latest revision]. Standard Methods of Testing Flexible Cellular Materials – Slab, Bonded, and Molded Urethane Foam.

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Industries' knowledge or obtained from sources believed by Technicon Industries to be accurate, and Technicon Industries does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.